

TECHNICAL DATA SHEET

LevelMore Contract

23/02/26

A free-flowing, fast-setting, 2-part levelling and smoothing compound



Key Features

- Designed for use on solid bases, including heated screeds
- Outstanding workability and flow
- Sets with a smooth, consistent surface finish
- Protein-free formulation with high dimensional stability

Technical Information

Classification (EN 13813)		CT-C20-F7
Unit size		20kg bag & 4.5 litres pouch
Application temperature (air and background)		≥ 5°C
Application thickness		2-12mm
@20°C	Working time Walk on Tile after Fit resilient floor coverings after	30 minutes 2 hours 4 hours 6 hours
Consumption per mm thickness		Approximately 1.58kg /m ²
Flow rate using a 30mm Ø x 50mm flow ring (EN 12706)		140-150mm
Compressive strength	After 1 day After 7 days After 28 days	>9 N/mm ² >14 N/mm ² >20 N/mm ²
Flexural strength	After 1 day After 7 days After 28 days	>3 N/mm ² >5 N/mm ² >7 N/mm ²
VOC emissions	Low – Conforms to Eurofins Indoor Air Comfort criteria	

Areas of Use

Floors	Interior	Domestic and Commercial	Solid Bases	Heated Screeds
--------	----------	-------------------------	-------------	----------------

Background and Surface Preparation

Backgrounds must be sufficiently dry and strong enough to carry the total weight being applied. All surfaces must be clean, sound and free from contaminants that could impair adhesion, such as dust, dirt, oil, grease, laitance, and curing agents.

Suitable Floor Backgrounds			PRIMER REQUIRED
A Cement:Sand Screed (inc. Heated)	A Concrete	A Tile Backer Boards (on solid bases)	PrimeMore Universal
B Asphalt (Flooring Grade)	B Epoxy DPM	B Existing Ceramic, Porcelain, and Natural Stone Tiles (on solid bases)	PrimeMore Grip
C Calcium Sulphate/Anhydrite Screed (inc. Heated)			PrimeMore CS
A Prime with PrimeMore Universal diluted 1:3 with water. Depending on the porosity of the background, additional diluted coats may be required.		B Prime with one neat, undiluted coat of PrimeMore Grip.	C Prime with one neat, undiluted coat of PrimeMore CS.

The primer must be allowed to dry before applying LevelMore Contract.

Guidance Notes on Suitable Floor Backgrounds

Prime the following backgrounds with PrimeMore Universal, diluted 1:3 by volume with clean water (1 part primer to 3 parts water). Depending on the porosity of the background, additional diluted coats may be required. All coats must be touch dry before applying additional coats or the flooring compound.

CEMENT:SAND SCREED

Tile-Fixing (Porcelain & Ceramic):

- Allow new screeds to dry for at least 3 weeks.
- Direct fixing of agglomerate and some natural stone tiles will require extended drying times.
- For proprietary screeds, follow the manufacturer's recommendations for preparation and drying times.

Fitting Resilient Floor Coverings:

- Ensure the screed has an effective structural damp proof membrane and is dry ($\leq 75\%$ RH).
- If a structural damp proof membrane is absent or ineffective, apply One Coat DPM *Fast* or One Coat DPM *Trade* to the surface.
- PrimeMore MVS may be used where residual construction moisture is present up to 95% RH, whilst One Coat DPM *Fast* and One Coat DPM *Trade* are suitable for use up to 98% RH.

HEATED CEMENT:SAND SCREED

- New screeds must be commissioned from 3 weeks after screed installation and before work commences.
- Heat slowly at a maximum rate of 5°C per day until the maximum operating temperature is reached. Hold this temperature for 3 days before allowing the screed to cool to room temperature.

- For proprietary screeds, follow the manufacturer's recommendations for commissioning and preparation.

Fitting Resilient Floor Coverings:

- After commissioning, continue to run the underfloor heating until the screed is confirmed dry ($\leq 75\%$ RH).
- PrimeMore MVS may be used on prepared and commissioned heated screeds where residual construction moisture is present up to 85% RH. Alternatively, One Coat DPM *Fast* and One Coat DPM *Trade* may also be used on prepared and commissioned heated screeds.
- The underfloor heating should be switched off 48 hours prior to commencing work.

CONCRETE

Tile-Fixing (Porcelain, Ceramic, & Natural Stone):

- Allow new concrete to cure before being subjected to continuous air drying in good conditions for at least 6 weeks.
- Power floated concrete should be mechanically prepared to achieve a clean, sound, micro-textured, dust-free surface.

Fitting Resilient Floor Coverings:

- Ensure all concrete, including power floated concrete, has an effective structural damp proof membrane and is dry ($\leq 75\%$ RH).
- If a structural damp proof membrane is absent or ineffective, apply One Coat DPM *Fast* or One Coat DPM *Trade* to the surface.
- PrimeMore MVS may be used where residual construction moisture is present up to 95% RH, whilst One Coat DPM *Fast* and One Coat DPM *Trade* are suitable for use up to 98% RH.

Continued on next page...

- Power floated concrete must also be mechanically prepared to achieve a clean, sound, micro-textured, dust-free surface.

TILE BACKER BOARDS

- Must be installed as instructed by the manufacturer and be securely fixed to suitable, prepared solid bases.
- Ensure the adhesive used to fix the boards has fully set before commencing work.
- Please note that some proprietary board manufacturers may specify a minimum compound thickness when installing certain floor coverings to prevent point-loading issues.

Prime the following backgrounds with one neat, undiluted coat of PrimeMore Grip. Allow the primer to dry before applying the flooring compound.

FLOORING GRADE ASPHALT

- Must be hard, sound and firmly adhered.

EPOXY DPM

- Must be a flooring grade that is compatible with cementitious products.
- Ensure it is hard, sound and firmly adhered.

EXISTING CERAMIC, PORCELAIN, AND NATURAL STONE TILES

- Must be in good condition, free from contaminants and well bonded.
- Ensure the existing structure can take the additional weight.

Fitting Resilient Floor Coverings:

- If the existing tiles are fixed to a subfloor that does not contain an effective structural damp proof membrane, Kelmore DPM must be applied to the surface of the prepared tiles.

Prime calcium sulphate/anhydrite screeds with one neat, undiluted coat of PrimeMore CS. Allow the primer to dry before applying the flooring compound.

CALCIUM SULPHATE/ANHYDRITE SCREED

- All laitance and surface contaminants must be completely removed.

Tile-Fixing (Porcelain, Ceramic, & Natural Stone):

- The screed must be confirmed adequately dry ($\leq 85\%$ RH).

Fitting Resilient Floor Coverings:

- The screed must be confirmed dry ($\leq 75\%$ RH).

HEATED CALCIUM SULPHATE/ANHYDRITE SCREED

- All laitance and surface contaminants must be completely removed.
- New heated screeds must be commissioned from 7 days after screed installation and before work commences.
- The screed should be heated slowly and in accordance with the recommendations of the screed manufacturer.

Tile-Fixing (Porcelain, Ceramic, & Natural Stone):

- The screed must be confirmed adequately dry ($\leq 85\%$ RH).
- Switch off underfloor heating 48 hours prior to commencing work.

Fitting Resilient Floor Coverings:

- After commissioning, continue to run the underfloor heating until the screed is confirmed dry ($\leq 75\%$ RH).
- Switch off underfloor heating 48 hours prior to commencing work.

ADDITIONAL INFORMATION

Underfloor Heating: LevelMore Contract can be used to encapsulate electric underfloor heating cables which have been adhered to prepared floors. For resilient floor coverings, it should be applied at the thickness recommended by the manufacturer to ensure the floor covering does not suffer heat damage.

After completing installations on backgrounds incorporating underfloor heating, the heating system should not be run for 10 days. Following this period, the floor temperature must be gradually raised to its optimal operating temperature, with an increase of no more than 2°C per day.

Impervious Backgrounds: To provide an absorbent base for the application of adhesives, when fitting resilient floor coverings, LevelMore Contract must be applied at a minimum thickness of 3mm.

Multiple Layers: Where possible, LevelMore Contract should be applied at the desired thickness in a single application. If required, additional layers - which must not exceed the thickness of the previous layer - may be applied once the compound is walkable and primed with diluted PrimeMore Universal.

Protein-Free: LevelMore Contract is suitable for use in biologically sensitive areas.

Mixing

LevelMore Contract is a 2-part product; LevelMore Contract powder must only be mixed with LevelMore Contract liquid at a ratio of 20kg powder to 4.5 litres liquid.

Pour the LevelMore Contract liquid into a clean bucket. Gradually add the powder whilst mixing thoroughly with an electric paddle mixer until a smooth, lump-free consistency is achieved. The compound is ready for use immediately after mixing.

Application

Pour the mixed compound onto the prepared floor, then use a trowel, rake or pin leveller to regulate the thickness and guide the product into the desired areas. If the applied thickness allows, a spiked roller may be used within the working time to remove any trapped air and further enhance the surface finish.

Pumped Application

Mix according to the pump manufacturer's recommendations ensuring the correct water ratio is maintained. The mixed product should be smooth and fluid and have no surface separation or bleed. Flow checks should be performed regularly during the pumping process.

Drying

Drying times will vary dependent on the porosity of the background, ambient temperature and humidity. When tested to the industry standard temperature of 20°C, LevelMore Contract can be walked on after 2 hours. Porcelain, ceramic, and natural stone tiles after can be fixed after 4 hours, and resilient floor coverings can be installed after 6 hours. Please note that higher temperatures and low humidity will accelerate drying, whilst lower temperatures and high humidity will delay it.

Coverage

Coverage will vary dependent on the texture of the background and the application thickness of the product. The table below shows the approximate coverage of a 20kg bag of LevelMore Contract when mixed with 4.5 litres of LevelMore Contract liquid.

Application Thickness	2mm	3mm	5mm	10mm	12mm
Approximate Coverage	6.3m ²	4.2m ²	2.5m ²	1.26m ²	1.05m ²

Notes:

- Cementitious products should only be used when both air and background temperatures are 5°C or higher. If the temperature falls below 5°C, the chemical reaction required for the product to set is hindered, dramatically slowing the curing process. Normal setting will only resume once temperatures rise. However, if temperatures drop below freezing before the product has fully set, the integrity and performance of the product will be compromised.

Cleaning: All tools should be cleaned with water after use and before the product sets.

Health and Safety: For full details, please refer to the Safety Data Sheet, available at www.kelmore.co.uk or by contacting Kelmore Ltd.

Storage and Shelf Life: When stored in unopened packaging, off the ground, and in cool, dry conditions, this product has a shelf life of 12 months.

BS & EN Standards: Product should be used in accordance with the requirements of the relevant British and European Standards.

All the information supplied by Kelmore Ltd is offered in good faith and is derived from the company's combined knowledge, experience and testing. Without prior notice, due to on-going research and development, the information we offer can be updated at any time. Kelmore's products are developed, tested and manufactured to consistently high standards, however, we accept no liability for any loss or damage which may arise from factors outside of our control, such as site conditions and/or the execution of the work.



EN 13813: CT-C20-F7

 **Kelmore**

LevelMore Contract